

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 60-131765

(43)Date of publication of application : 13.07.1985

(51)Int.Cl.

H01M 4/52

(21)Application number : 58-240140

(71)Applicant : MATSUSHITA ELECTRIC IND CO LTD

(22)Date of filing : 20.12.1983



(72)Inventor : MATSUMOTO ISAO  
TSUDA SHINGO  
KAIYA HIDEO  
TSUBOI RYOJI  
IKEYAMA SHOICHI  
YAMAGA MINORU

## (54) NICKEL POSITIVE ELECTRODE FOR BATTERY

### (57)Abstract:

PURPOSE: To make a manufacturing process steady by forming a nickel positive electrode by impregnating a mixture mainly comprising nickel hydroxide powder having spherical shape in a dry state or a paste state into a substrate.

CONSTITUTION: Flake-shaped NaOH powder is put into nickel sulfate solution in a stirring tank, and they are stirred and aged at about 40° C to form nickel hydroxide powder 1 having a spherical or similar form and a mean particle size of 1 ~ 100 $\mu$ m. The nickel hydroxide powder 1 is mixed with nickel powder, cobalt powder, and water to form paste. The paste is sprayed and filled in a foam metal 2 or mixture of the powder 1 and graphite is filled in a metal pockets 3 having a number of fine pores 4 to form a nickel positive electrode. Since spherical nickel hydroxide powder is used, coming off of the powder or unsteady paste fluidity is eliminated, and a manufacturing process is made steady.



## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]